

CHWEN SHYANG ENTERPRISE CO., LTD.



純祥實業股份有限公司

NO.13, RONG-GONG N.RD., GUANN-IN INDUSTRIES
PARK, TAUR-YUAN, TAIWAN 328

TEL : 886 3 4389676

FAX : 886 3 4389686

WEBSITE :

<http://www.shm.com.tw>

EMAIL :

bonach.a001@bonalight.com.tw

SPECIFICATION:

保護膜(Protective Film)

ITEM NO: Z180P

基材：聚乙烯對苯二甲酸酯 (PET film)

Color : Transparent

物性資料：

檢驗項目 (Items)	單位 (Units)	品管檢測標準 (QC)	測試數據 (Data)
總厚度	mm	0.175±5%	0.171
Total thickness	mil	7.0	6.84
基材厚度	mm	0.100	0.100
Base film thickness	mil	4	4
抗張強度	Mpa	原膜基礎特性	*****
Tensile strength			
伸長率	%	原膜基礎特性	*****
Elongation			
鋼板黏着力	g/25mm	10±5	10
Adhesion to Steel			
初期力	g/25mm	15±5	12
Initial adhesive force			
透光度	%	88%±5%	88%
VLT%			
表面硬度	H	3H	3H ↑
Hardness			
表面阻抗	歐姆 Ω	10 ⁸	Non-Treatment

PROTECTIVE FILM

ITEM NO: Z180P (2 LAYER)




CHWEN SHYANG ENTERPRISE CO., LTD.

Screen Protectors (Protective Film Series)

Applications series



Most of people think about that screen protector can be protect the screen like scratches but affect the clarity of screen. But now,  Products brought you the new technology on the new edition of the screen protector .

<http://www.shm.com.tw/Protective.htm>

Contact Person : Wilson Chou



純祥實業股份有限公司

卓明鈺

行動: 0936-050432
 TEL: (03) 438-9676~7 • 438-9687
 FAX: (03) 438-9686 統編: 86576236
 地址: 桃園縣觀音鄉觀音工業區榮工北路13號
 Web Site: <http://www.bonalight.com.tw>
 E-mail: bonach.a001@bonalight.com.tw



彩色紙品上光塗料權威



CHWEN SHYANG ENTERPRISE CO., LTD.

BONA LIGHT

Wilson Chou

No. 13, Rong-Gong N. Rd., Guann-In Industries Park,
 Taur-Yuan, Taiwan 328 R. O. C.

Mobil: 886-936-050432
 TEL: 886-3-438-9676~7 • 886-3-438-9687 Fax: 886-3-438-9686
 Web site: <http://www.bonalight.com.tw>
 E-mail: bonach.a001@bonalight.com.tw
 MSN: wilson_chou@hotmail.com



Leading company of printing varnish
 for printed paper substrates