



CHWEN SHYANG ENTERPRISE CO., LTD.

純祥實業股份有限公司

NO.13, RONG-GONG N.RD., GUANN-IN INDUSTRIES PARK, TAUR-YUAN, TAIWAN 328

TEL : 886 3 4389676

FAX : 886 3 4389686


WEBSITE :

<http://www.shm.com.tw>

EMAIL :

bonach.a001@bonalight.com.tw

CHWEN SHYANG ENTERPRISE CO., LTD					
	20°C	25°C	30°C	35°C	40°C
CH-20419	20.09	19.53	19.09	18.43	17.7
CH-20402E	18.68	17.97	17.7	17.36	17.08
CH-20420	17.4	17.18	17.08	16.82	16.12
CH-905	32.6	31.13	29.13	28.59	26.5
Korea	16.8	16.37	16.06	15.8	15.78



Testing conditions as below:


Testing Paper Sample is 5 colors art paper (180 Lbs & 350 Lbs), respectively affixed gloss & mat BOPP film

Laminating thickness is 13.70 *um*

Tear membrane angle is 180 degrees

Test unit is "grams"

All data value is average.



Date of Nov/09/2007